

BIOHEL

Bio wooden surfaces are treated with products based on vegetable or mineral oils, natural waxes and/or resins.

Such surfaces could not be direct compared to lacquered ones. Bio oils mostly penetrate into wood structure – to prevent and increase surface resistant, and beside this gives wood a strong esthetical effect.

BIOHEL



Recommended restoring
at least 2x per year

Recommendation: To avoid unpleasant smell of drying oil in the beginning, we recommend daily room ventilation for a couple of days.

Interval of renewing mostly depends on exposition of wooden surfaces – we recommend it once to twice a year.

Warning: Natural vegetable oils dry oxidatively, which is an exothermic process (release of heat). **With oils soaked papers or textile cloths must be burned or soaked with water to prevent self-ignition.**

BIOHEL

MAINTENANCE INSTRUCTIONS



Helios TBLUS d.o.o.
Količevo 65, 1230 Domžale, Slovenia
T +386 1 722 40 00
E wood.coatings@helios.si
www.helios-woodcoatings.com

Member of  KANSAI HELIOS Part of  KANSAI PAINT

392576 Ver. 03



MAINTENANCE AND RENOVATION INSTRUCTIONS OF OILED AND WAXED WOODEN SURFACES

For the daily care it is enough to clean the wooden surfaces with a dry or slightly wet cotton cleaning cloth. Don't use any microfiber cloths, fat dissolving detergents or steam cleaners. At least twice a year we recommend maintenance with **BIOHEL oil** to refresh the surface. Beside visual effect this is needed to protect the surface and pores from dirt and to improve resistance against beverage spillage and discoloration of wood.

Objects that are sharp, hot or wet can damage the wooden surfaces. Spilled liquids should be removed instantly.

Always move the product with care by lifting it instead of dragging, and carefully setting it down. This will preserve the integrity of the joints. Avoid placing wooden furniture next to a source of heat or in direct sunlight. This can cause dryness, cracking and fading of the color. Avoid extreme humidity levels in your home, as furniture woods don't take kindly to excessively dry air or extremely high humidity. To protect your solid oak furniture, use a humidifier and/or air conditioner



Restoring of oiled wood furniture in natural and environmentally friendly way

to maintain an air humidity level in your home between 40 and 70 percent.

Maintenance and renovating process suggestion:

1. Cleaning and protecting the surface

First clean the surface with water logged cloth. In case the furniture is made of oak or ash we recommend additional cleaning with a very soft brush to clean the pores if needed.

After drying carefully sand with fine scotch-brite or very fine sanding paper (P 400 or higher) if needed. Sanding must be carried out evenly and in the way of the wood growth to avoid differences in the final appearance and sheen. In case of stained wood only polishing with scotch-brite is recommended.

Remove the dust.



Silky appearance, smooth waxy touch and water-repellency

2. Oiling

With oil logged textile cloths apply **BIOHEL oil** over the surface. After short period of time (approx. 2-5 min) remove surplus oil with dry textile cloth (wipe off).

Light handle polishing in wood fibre direction with soft cloth is recommended to achieve unique esthetic surface. Drying for at least 24 hours.

In case of raised wood grain polish the surface with cotton cloth after drying. Depending on surface condition, apply one more layer if needed.

