


SOFT TOUCH EFFECT







The wooden surface is prepared by sanding using P180 – P220 sanding paper.

Then follows lacquering with Heliodur base enamel. Normally, air spraying is needed in two coats. In-between coats we sand using granulation paper P280-320.





Then we apply Heliodur enamel in the selected colour. Dry at room temperature (18-23°C) 4-6 hours.



Effects of different colour shades can be prepared according to different colour cards (RAL, Monicolor, NCS etc.)



Helios TBLUS, d.o.o. Količevo 65, 1230 Domžale, Slovenia T +386 1 722 40 00 E wood.coatings@helios.si www.helios-woodcoatings.com







